

FLUXO 408

Fluorescent Magnetic Concentrate for Magnetic Particle Inspection

General Appearance & Composition

- Water Based Fluorescent Magnetic Concentrate for Magnetic Particle Inspection
- Typical Dilution:
 - 1kg of **FLUXO 408** for 50L to 100L of water
 - 1.0% to 2.0% in Water
- Processing Temperature: 0°C to 50°C
- **FLUXO 408** is a mixture of fluorescent magnetic powder, wetting agent, antifoam, rust inhibitor and additives.
- Excellent sharp, quick and stable indications
- Low Fluorescence background on parts.
- NON-DANGEROUS product
- Manufacturer: SREM TECHNOLOGIES

Approval & Specifications

- EN ISO 9934-2
- AMS 3044 (Fluorescent Powder) - AS 4792
- ASTM E1444 / E1444M - ASTM E-709
- ASME BOILER AND PRESSURE VESSEL CODE, SECTION V
- Code RCC-M

Properties

- Performance: 70mm in reference block Type 2
- Aspect & color: green suspension
- Particle size: around 5-10 µm
- Fluorescence coefficient : $\beta \approx 3,8 \text{ cd.W}^{-1}$
- Corrosion test: level 1 (according to standard ISO 9934-2)
- Mechanic stability : stable product
- Stability in time: minimum 24 months
- Settlement Volume: around 0,3 ml / 100 ml (1h)

Application

- Remove tinder, rust and other contaminations from surface
- Shake concentrate well before use
- Typical dilution: 1 to 2% in water
- During magnetization spray the preparation on the surface
- Defects will appear as yellow-green fluorescent indications under UV Light

Shelf Life

- Minimum of 2 years for drums - stored at room temperature.
- Please refer to the Safety Data Sheet

Pack Sizes

- Drum 1kg / Drum 5kgs



Version: 0410-2025